## PRODUCTION OF METAL CASTINGS

Patent Number:

GB2063126

Publication date:

1981-06-03

Inventor(s):

Applicant(s)::

**FOSECO INT** 

Requested Patent:

WO8002811

Application

Number:

GB19800040649 19800418

**Priority Number** 

(s):

GB19790020757 19790614

IPC Classification: B22D27/04; B22D7/10; B22D35/04

EC Classification: B22C9/08, B22D7/10B, B22D27/04

Equivalents:

#### **Abstract**

Sound castings (1), free from aluminium pick-up, are produced in moulds (2) in which are located at places where it is desirable to promote directional solidification lining pads (9) made from a composition which comprises particulate refractory material, finely divided aluminium, an oxidising agent for the aluminium and a binder, and which is substantially free of fluoride salts, which contains a fibrous refractory material and which has a density of 0.3 to 1.1 g/cms. The composition may be incorporated as a preformed pad, or as a flexible mat or mouldable mixture which can be dried or hardened chemically.

Data supplied from the esp@cenet database - 12

# **PCT**

# EP. 0030940 WORLD INTELLECTUAL PROPERTY ORGANIZATION International Ruseau



# INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>3</sup> : B22D 27/04, 35/04, 7/10	A1	<ul><li>(11) International Publication Number: WO 80/02811</li><li>(43) Internati nal Publication Date: 24 December 1980 (24.12.80)</li></ul>
(21) International Application Number: PCT/GB80/00067 (22) International Filing Date: 18 April 1980 (18.04.80)		Foseco Minsep International Limited, 285 Long Acre,
(31) Priority Application Number:  (32) Priority Date: 14 June 1979 (	79207. 14.06.7	GB, JP, US.
(33) Priority Country:	G	Published  With international search report
<ul> <li>(71) Applicant (for all designated States except US): FOSECO INTERNATIONAL LIMITED [GB/GB]; 285 Long Acre, Nechells, Birmingham B7 5JR (GB).</li> <li>(72) Inventor; and</li> <li>(75) Inventor/Applicant (for US only): GOUGH, Michael, John[GB/GB]; 3 Uplands Close, Penkridge, Staffordshire (GB).</li> </ul>		ng   el,

## (54) Title: PRODUCTION OF METAL CASTINGS

### (57) Abstract

Sound castings (1), free from aluminium pick-up, are produced in moulds (2) in which are located at places where it is desirable to promote directional solidification lining pads (9) made from a composition which comprises particulate refractory material, finely divided aluminium, an oxidising agent for the aluminium and a binder, and which is substantially free of fluoride salts, which contains a fibrous refractory material and which has a density of 0.3 to 1.1 g/cm3. The composition may be incorporated as a preformed pad, or as a flexible mat or mouldable mixture which can be dried or hardened chemically.

